

FIG. 1






FIG. 2B



2/12




FIG. 3A




FIG. 3B




FIG. 3D









FIG. 3F

3/12

FIG. 3C*FIG. 3E*

**FIG. 4A****FIG. 4B****FIG. 4C**

5/12




FIG. 4D








FIG. 4E




6/12

**FIG. 5A****FIG. 5B**



7/12

**FIG. 6****FIG. 8**

8/12

FIG. 7A**FIG. 7C****FIG. 9C**

9/12

**FIG. 7B****FIG. 7D**




FIG. 9A




FIG. 9B




FIG. 9D

FIG. 9E










FIG. 9F

11/12

FIG. 10A**FIG. 11**

<u>Treatment</u>	<u>TAr (mm²)</u>	<u>BAr (mm²)</u>	<u>BAr % TAr</u>
Vehicle (n=6)	2135.4 ± 415.8	892.7 ± 279.9	41.0 ± 6.1
22R+20S (n=6)	1730.9 ± 409.5	850.3 ± 202.6	49.3* ± 4.2

FIG. 12A**FIG. 12B**0.2 mm

**FIG. 10B****FIG. 10C**